



# Bulk Asbestos Material Analysis

(EPA Method 600/R-93/116, Point Count Analysis)

Sample Company  
Sample Contact  
000 Sample Street  
Suite 000  
Sample City, CA 00000

**Client ID:** 0000  
**Report Number:** N000000  
**Date Received:** 00/00/0000  
**Date Analyzed:** 00/00/0000  
**Date Printed:** 00/00/0000

**Job ID/Site:** Sample Site

**FALI Job ID:** 0000-0  
**Total Samples Submitted:** 3  
**Total Samples Analyzed:** 3

**PLM Report Number:** N/A

### Sample Preparation and Analysis:

Each sample was prepared using the gravimetric technique. A representative subsample was weighed, ashed for eight hours, and reweighed to determine the proportion of the organic component. The ashed residue was ground in concentrated hydrochloric acid, dried and reweighed to determine the acid-soluble component weight percentage. The residual material was analyzed for asbestos using polarized light microscopy. Asbestos quantitation was performed using the semi-quantitative Point Count method following the general guidelines in EPA Method 600/R-93/116. The analytical sensitivity for the method is calculated as the asbestos concentration that results from one point counted in the analysis adjusted using the residual weight of the sample. The limit of detection for this method has not been determined.

Sample ID	Lab Number	Sample Description
-----------	------------	--------------------

**1** 00000000 **White Plaster**

*Point Count Results:*

Number of asbestos points counted: 2  
Number of non-empty points: 1000  
**Percent asbestos in layer: 0.15**  
Analytical sensitivity (%): 0.08  
Asbestos type(s) detected: Chrysotile

*Gravimetry Results:*

Organic weight percentage: 10.72  
Acid-soluble weight percentage: 12.45  
Residual weight percentage: 76.82

Comment:

**2** 00000000 **White Plaster**

*Point Count Results:*

Number of asbestos points counted: 3  
Number of non-empty points: 1000  
**Percent asbestos in layer: 0.23**  
Analytical sensitivity (%): 0.08  
Asbestos type(s) detected: Chrysotile

*Gravimetry Results:*

Organic weight percentage: 10.29  
Acid-soluble weight percentage: 12.85  
Residual weight percentage: 76.85

Comment:



# Bulk Asbestos Material Analysis

(EPA Method 600/R-93/116, Point Count Analysis)

Sample Company  
Sample Contact  
000 Sample Street  
Suite 000  
Sample City, CA 00000

**Client ID:** 0000  
**Report Number:** N000000  
**Date Received:** 00/00/0000  
**Date Analyzed:** 00/00/0000  
**Date Printed:** 00/00/0000

**Job ID/Site:** Sample Site

**FALI Job ID:** 0000-0  
**Total Samples Submitted:** 3  
**Total Samples Analyzed:** 3

**PLM Report Number:** N/A

### Sample Preparation and Analysis:

Each sample was prepared using the gravimetric technique. A representative subsample was weighed, ashed for eight hours, and reweighed to determine the proportion of the organic component. The ashed residue was ground in concentrated hydrochloric acid, dried and reweighed to determine the acid-soluble component weight percentage. The residual material was analyzed for asbestos using polarized light microscopy. Asbestos quantitation was performed using the semi-quantitative Point Count method following the general guidelines in EPA Method 600/R-93/116. The analytical sensitivity for the method is calculated as the asbestos concentration that results from one point counted in the analysis adjusted using the residual weight of the sample. The limit of detection for this method has not been determined.

Sample ID	Lab Number	Sample Description
3	00000000	<b>White Plaster</b>
<i>Point Count Results:</i>		<i>Gravimetry Results:</i>
Number of asbestos points counted:	2	Organic weight percentage: 10.57
Number of non-empty points:	1000	Acid-soluble weight percentage: 13.61
<b>Percent asbestos in layer:</b>	<b>0.15</b>	Residual weight percentage: 75.82
Analytical sensitivity (%):	0.08	
Asbestos type(s) detected:	Chrysotile	

Comment:

Laboratory Supervisor, Hayward Laboratory

Analytical results and reports are generated by Forensic Analytical Laboratories Inc. (FALI) at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by FALI to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by FALI. The client is solely responsible for the use and interpretation of test results and reports requested from FALI. Forensic Analytical Laboratories Inc. is not able to assess the degree of hazard resulting from materials analyzed. FALI reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified. All samples were received in acceptable condition unless otherwise noted.